



Garment films designed for Textiles



Product	Colours	Pressing Time & Temperature	Peel?	Wash & Care	Description	Available Sizes
Hotmark	Standard	15-20 seconds at 150-160°C with medium to high pressure*	Cold	80°C	Matte polyurethane garment film suitable for fine detail logos - thin and soft!	50cm x 1m
Hotmark	Fluorescent	15-20 seconds at 150-160°C with medium to high pressure*	Cold	80°C	Matte polyurethane garment film suitable for fine detail logos - thin and soft!	50cm x 1m
Hotmark	Gold & Silver	15-20 seconds at 150-160°C with medium to high pressure*	Cold	Handwash	Matte polyurethane garment film suitable for fine detail logos - thin and soft!	50cm x 1m
Fashion Flex	Wild Designs	15-20 seconds at 150-160°C with medium to high pressure*	Cold	40°C	Fashionable wild print designs perfect for backgrounds, graphics and text!	50cm x 1m
FlexCut sticky	Standard	17 seconds at 165°C with medium to high pressure*	Hot	60°C	Thin and stretchable garment film with a matte finish - easy to cut & weed!	A4
FlexCut sweet	Standard	17 seconds at 165°C with medium to high pressure*	Warm	60°C	Garment film with a matte screen-printed like finish - very thin, stretchable & soft!	50cm x 1m
FlexCut PUFF	Standard	15 seconds at 180°C or 20 seconds at 160°C* with variable pressure**	Hot or Cold**	40°C	Garment film with a bubbly 3-dimensional texture! - Great for retro vintage looks.	50cm x 1m

*Medium pressure is recommended for cotton and higher pressure is recommended for polyester.

**Using less pressure and peeling whilst hot will increase the height of the 3D effect.



01628 898070



hello@yolo.co.uk



www.yolo.co.uk